

# KEP 2380



## Ethylene Propylene Diene Terpolymer

KUMHO POLYCHEM

### Product Data Sheet

Product Description	Features
KEP2380 is an EPDM rubber with Bimodal molecular weight distribution, low ethylene contents. It can be used to 60 ~ 70 Shore A dense body sealing, Radiator hose, molded goods, gaskets.	<ul style="list-style-type: none"><li>- High loadability</li><li>- Superior processability</li><li>- Good cure performance</li><li>- Fast curing for continuous vulcanization</li><li>- Improves productivity &amp; collapse resistance</li></ul>

Test items	Sale Specifications	Unit	Test Method
Volatile Matter	Max 0.75	wt %	ASTM D5668
Mooney Viscosity ML(1+8)@125 °C	82.0 ± 5.0	MU	ASTM D1646
Ethylene Contents	55.5 ± 2.0	wt %	ASTM D3900
ENB Contents	5.7 ± 0.5	wt %	ASTM D6047

### Other Products Features

<b>Product Form</b>	Bale
<b>Packaging</b>	25 kg/Bale in Carton/Mesh Box, LDPE film, 750 kg(25 kg × 30),
<b>Shelf Life</b>	24 months from date of production at room temperature in dry condition, exposure to light has to be avoided
<b>The Others</b>	RoHS Free

### Contact Information

<b>Head Office</b>	8F, East Wing, Signature Tower, #100 Cheonggyecheon-ro, Jung-gu, Seoul, Korea 82-2-6961-0000
<b>Plant</b>	613 Sandanjungang-ro, Yeosu, Jeonnam, Korea 82-61-688-2822
<b>Revision Date</b>	05/01/2016
<b>Revision No.</b>	11