

Ethylene Propylene Diene Terpolymer



Product Description		Features	
KEP350 is an EPDM rubber with Medium molecular weight distribution, low ethylene, high ENB. It can be used to Cover strips, white sidewalls, window seals, gaskets, packing, and sponge.		 Medium Mooney viscosity with excellent Processability Ultra fast vulcanization speed. Suitable for blends with diene type rubbers 	
Test items	Sale Specifications	Unit	Test Method
Volatile Matter	Max 0.75	wt %	ASTM D5668
Mooney Viscosity ML(1+4)@125 ℃	56.0 ± 6.0	MU	ASTM D1646
Ethylene Contents	56.5 ± 3.5	wt %	ASTM D3900
ENB Contents	7.9 ± 1.0	wt %	ASTM D6047
Other Products Fea	atures		
Product Form	Bale		
Packaging	25 kg/Bag Mesh Box, LDPE film 900 kg(25 kg × 36)	۱,	
Shalf Lifa	24 months from date of produ	ction at room t	emperature in dry

Shelf Life24 months from date of production at room temperature in dry
condition, exposure to light has to be avoided

The Others RoHS Free

Contact Information

Head Office	8F, East Wing, Signature Tower, #100 Cheonggyecheon-ro, Jung-gu, Seoul, Korea 82-2-6961-0000
Plant	613 Sandanjungang-ro, Yeosu, Jeonnam, Korea 82-61-688-2822
Revision Date	12/02/2020
Revision No.	4



KUMHO POLYCHEM